



ecopoxysystems™

A Division Of Oceanearring Research and Development
26 Putnam Ave. Johnston RI. 02919
www.ecopoxysystems.com **1-877-ECO-POXY**

Exotherm Analysis (Part1)

Time	Temp
0:15	31.6
0:30	41
0:45	53.2
1:00	62.6
1:15	69.2
1:30	78
1:45	87.2
2:00	91.8
2:15	128.4
2:30	159.6
2:45	163.2
3:00	157.2
3:15	155.2
3:30	155.2
3:45	148.2
4:00	145.6
4:15	141.8
4:30	140.4
4:45	139.6
5:00	138
5:15	137.2
5:30	136.6
5:45	134.8
6:00	131.6
6:15	130.4
6:30	130
6:45	129
7:00	128.4
7:15	127.4
7:30	126.6
7:45	125.6
8:00	125.4
8:15	125.6
8:30	123.6
8:45	123.8
9:00	122
9:15	123.6
9:30	122
9:45	122.4
10:00	119.4
10:15	119.8

Exotherm Analysis (Part 2)

Time	Temp
10:30	120.2
10:45	118
11:00	116.4
11:15	117
11:30	115.2
11:45	114.6
12:00	114.2
12:15	113.4
12:30	118.8
12:45	116.8
13:00	115.8
13:15	114.6
13:30	113.8
13:45	112
14:00	112.8
14:15	114
14:30	114.21
14:45	114.4
15:00	110
15:15	111
15:30	112
15:45	110
16:00	110
16:15	109
16:30	107
16:45	104
17:00	106
17:15	105
17:30	108
17:45	105
18:00	105.4
18:15	105
18:30	105.2
18:45	102
19:00	104.4
19:15	104.4
19:30	104.4
19:45	102.4
20:00	102
20:15	102